

9090 X9 Superfast

Fast Anti-Scratch Clear Coat

silco[®]

Fast clear coat for various applications.

- / Exceptionally fast drying
 - Only 5 minutes at 60°C
 - 60 minutes at 20°C
- / Only 5 minutes at 60°C
- / Immediate polishing after cooling down
- / Perfect gloss retention & UV protection
- / In the base coat no hardener/activator is needed



9090 X9 Superfast

Fast Anti-Scratch Clear Coat

Mixing ratio 3:1

Hardener	Standard 9125	Slow 9127
Drying time*		
20°C/68°F	~60 min	~60 min
60°C/140°F	~5 min	~5 min
IR	~5 min	~5 min
Flash-off 20°C/68°F	5 min	
Potlife 20°C/68°F	60 min	
Thinner	0–5 % (7050 Standard, 7070 Slow)	

*Indicative times subject to hardener and thinner type/application/environment...

How to use?

Use of slow hardener is recommended in case of higher temperatures in combination with larger surfaces.

Use topcoat spraygun with 1.2–1.4 nozzle. Apply two full coats with maximum 5 minute flash off between coats.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

Highly productive HS clear coat X9 Superfast is characterised by outstandingly short drying times when baking (5 min/60°C) or when air drying (60 min/20°C). Polishing is possible immediately after cooling. Short drying times allow more turnover of vehicles and decreased manpower costs. Additionally, fast drying without oven baking allows fuel and electricity savings.

Packaging

9090 X9 Superfast
Fast Anti-Scratch Clear Coat

Prod. Nr.	Content
9090-1	1 L
9090-3	3 L

Hardener / 9125 - 9127 HS Hardener
HS Acrylic Hardener - mixing ratio 3:1

Prod. Nr.	Content	Description
9125-0,33 / 9125-0,5 / 9125-1 / 9125-2,5	330 ml / 500 ml / 1 L / 2.5 L	Standard
9127-0,5 / 9127-1 / 9270-2,5	500 ml / 1 L / 2.5 L	Slow